



SECTION 1006

AGGREGATE FOR SURFACING

1006.1 Scope. This specification covers aggregate to be used for surfacing.

1006.2 Aggregate for surfacing shall be composed of durable particles of rock. When tested in accordance with AASHTO T 96, the wear shall not exceed 60 percent. The deleterious substances shall not exceed the following values and the sum of percentages of all deleterious substances shall not exceed 12 percent.

Deleterious Material	Percent by Weight (Mass)
Deleterious Rock and Shale	12.0
Mud Balls	5.0
Other Foreign Material	2.0

1006.3 Aggregate shall be in accordance with the following for the grade specified in the contract:

Grade	Type of Material	Percent Passing					
		Sieve Sizes					
		1 in. (25.0 mm)	3/4 in. (19.0 mm)	3/8 in. (9.5 mm)	No. 4 (4.75 mm)	No. 10 (2.00 mm)	No. 200 (75 μm)
A ^a	Gravel	100	80-100	60 ^b	10-35	0-10
B ^a	Crushed Stone	100	65 ^b	5-25
C	Chat	100	80 ^b	45 ^b

^aType 1 Aggregate for Base may be used, except all material shall be in accordance with [Sec 1007](#).

^bIndicates maximum permitted.